Application No. 09/396,266 Docket No. 1998U007A.US Reply to Office Action Dated May 15, 2003

## Amendments to the Claims

This listing of claims will replace all prior versions, and listings, of claims in the application:

## Listing of Claims:

- 1-32 (Cancelled).
- 33. (Currently amended). A process for polymerizing olefins comprising contacting olefin(s) with a catalyst system comprising an activator and a catalyst precursor, wherein
  - (a) the activator is a neutral or ionic ionizing salt comprising a cation selected from the group consisting of triphenylcarbenium, dimethylanilinium, and trialkylammonium, and an anion selected from the group consisting of borate and aluminate; and
  - (b) the catalyst precursor is represented by:

## LM<sup>n</sup>X<sub>3</sub>

wherein M is a Group 4 metal;

- L is an unsubstituted or substituted indenyl, fluorenyl ligand or substituted cycloalkadienyl ligand except for pentamethylcyclopentadienyl;
- X is benzyl is selected from the group consisting of hydrogen, and unsubstituted and substituted versions of: aryl, alkyl, alkenyl, alkylaryl, and arylalkyl radicals having from 1-20 carbon atoms; and

n is 4.

Application No. 09/396,266 Docket No. 1998U007A.US Reply to Office Action Dated May 15, 2003

- 34. (Previously presented). The process of claim 33 wherein L is a substituted cycloalkadienyl excepting pentamethylcyclopentadienyl.
- 35. (Previously presented). The process of claim 33 wherein L is an unsubstituted or substituted indenyl or fluorenyl ligand.
- 36. (Previously presented). The process of claim 33 wherein the activator is a salt comprising a cation selected from the group consistent of triphenylcarbenium, dimethylanilinium, and trialkylammonium, and an anion that is a borate.
- 37. (Currently Amended). The process of claim 33 wherein the catalyst system is selected from the group consisting essentially of (MeCp)Zr(CH<sub>2</sub>Ph)<sub>3</sub>/triphenylcarbenium tetrakis(pentafluorophenyl)borate, (1,3-Me<sub>2</sub>Cp)Zr(CH<sub>2</sub>Ph)<sub>3</sub>/ triphenylcarbenium tetrakis(pentafluorophenyl)borate, (Fluorenyl)Zr(CH<sub>2</sub>Ph)<sub>3</sub>/ triphenylcarbenium tetrakis(pentafluorophenyl)borate, 2-(p-tolylindenyl)Zr(CH<sub>2</sub>Ph)<sub>3</sub>/ triphenylcarbenium tetrakis(pentafluorophenyl)borate, (1-trimethylsilyindenyl)Zr(CH<sub>2</sub>Ph)<sub>3</sub>(η<sup>6</sup>(PhCH<sub>2</sub>B(C<sub>6</sub>F<sub>5</sub>)<sub>3</sub>))/ triphenylcarbenium tetrakis(pentafluorophenyl)borate or (1,3-Me<sub>2</sub>Cp)Zr(CH<sub>2</sub>Ph)<sub>3</sub>trihexylammonium (1,3-Me<sub>2</sub>Cp)Zr(CH<sub>2</sub>Ph)<sub>3</sub>trihexylammonium (1,3-Me<sub>2</sub>Cp)Zr(CH<sub>2</sub>Ph)<sub>3</sub>/trihexylammonium tetrakis(pentafluorophenyl)borate.
  - (Currently amended). A catalyst system comprising an activator and a catalyst precursor, wherein
    - (a) the activator is a neutral or ionic salt comprising a cation selected from the group consisting of triphenylcarbenium, dimethylanilinium, and trialkylammonium, and an anion selected from the group consisting of borate and aluminate; and
    - (b) the catalyst precursor is represented by:

Application No. 09/396,266 Docket No. 1998U007A.US Reply to Office Action Dated May 15, 2003

## LM<sup>n</sup>X<sub>3</sub>

wherein M is a Group 4 metal;

- L is an unsubstituted or substituted indenyl, fluorenyl ligand or substituted cycloalkadienyl ligand except for pentamethylcyclopentadienyl;
- X is benzyl is selected from the group consisting of hydrogen, and unsubstituted and substituted versions of: aryl, alkyl, alkylaryl, and arylalkyl radicals having from 1 20 carbon atoms; and

n is 4.

- 39. (Previously presented). The catalyst system of claim 38 wherein L is a substituted cycloalkadienyl excepting pentamethylcyclopentadienyl.
- 40. (Previously presented). The catalyst of claim 38 wherein L is an unsubstituted or substituted indenyl or fluorenyl ligand.
- 41. (Currently Amended). The process catalyst of claim 38 wherein the activator is a salt comprising a cation selected from the group consisting of triphenylcarbenium, dimethylanilinium, and trialkylammonium, and an anion that is a borate.
- 42. (Currently Amended). The catalyst system of claim 38 selected from the group consisting essentially of (MeCp)Zr(CH<sub>2</sub>Ph)<sub>3</sub>/triphenylcarbenium tetrakis(pentafluorophenyl)borate, (1,3-Me<sub>2</sub>Cp)Zr(CH<sub>2</sub>Ph)<sub>3</sub>/ triphenylcarbenium tetrakis(pentafluorophenyl)borate, (Fluorenyl)Zr(CH<sub>2</sub>Ph)<sub>3</sub>/ triphenylcarbenium tetrakis(pentafluorophenyl)borate, 2-(p-tolylindenyl)Zr(CH<sub>2</sub>Ph)<sub>3</sub>/ triphenylcarbenium tetrakis(pentafluorophenyl)borate, (1-trimethylsilyindenyl)Zr(CH<sub>2</sub>Ph)<sub>3</sub>(η<sup>6</sup>(PhCH<sub>2</sub>B(C<sub>6</sub>F<sub>5</sub>)<sub>3</sub>))/ triphenylcarbenium tetrakis(pentafluorophenyl)borate or (1,3-Me<sub>2</sub>Cp)Zr(CH<sub>2</sub>Ph)<sub>3</sub>trihexylammonium (1,3-Me<sub>2</sub>Cp)Zr(CH<sub>2</sub>Ph)<sub>3</sub>/trihexylammonium tetrakis(pentafluorophenyl)borate.